

MATERIAL SAFETY DATA SHEET
FOR COATINGS, RESINS AND RELATED MATERIALS

Manufacturer: TRU-TEST Manufacturing Company
Address: 201 Jandus Road
Cary, IL 60013

Emergency Medical Info.: 1-800-228-5635 Ext. 017
Technical Information: 1-708-639-5383

Date of Preparation: January 3, 1995

Supersedes: July 25, 1990

SECTION I - PRODUCT IDENTIFICATION

Product Numbers: PE-Line PE-1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12 & OC
Product Name: TRU-TEST Enrich Wood Stain
Product Class: Interior Semi-Transparent Stain

SECTION II - HAZARDOUS INGREDIENTS

Ingredient/CAS. No.	WT %	Occupational Exposure Limits		Vapor Pressure mm Hg @ 20 ° C
		TLV	PPM PEL	
Mineral Spirits	64742-47-8	58-63	100ppm 500ppm	2.6

(S) = This ingredient is subject to the reporting requirements of SEC. 313 SARA Title III
NA = Not Applicable NE = Not Established

SECTION III - PHYSICAL DATA

Boiling Range	300-360° F	Vapor Density	x Heavier	Lighter than Air
Evaporation Rate	Faster	X	Slower than Ether	% Volatile Volume
Volatile Organic Content (VOC)	Less Than	525	gm/L	7.3 - 7.6 lbs

SECTION IV - FIRE AND EXPLOSION HAZARD DATA

FLAMMABILITY CLASSIFICATION

OSHA CLASS II FLASH POINT 105°F LEL 0.9
DOT COMBUSTIBLE LIQUID

EXTINGUISHING MEDIA:

☒ FOAM ☐ ALCOHOL FOAM ☒ CO2 ☒ DRY CHEMICAL ☒ WATER FOG ☐ OTHER

UNUSAL FIRE AND EXPLOSION HAZARDS: Closed containers may explode when exposed to extreme heat. Isolate from heat, sparks and open flames.

SPECIAL FIRE FIGHTING PROCEDURES: Treat as volatile liquid fire. Water spray may be ineffective. If water is used, fog nozzles are preferable.

SECTION V - HEALTH HAZARD DATA

EFFECTS OF OVEREXPOSURE: Severe eye irritation, drying of skin. Excessive inhalation causes headache, dizziness and nausea.

CARCINOGENICITY: None listed with NTP, IARC or OSHA.

MEDICAL CONDITIONS PRONE TO AGGRAVATION BY EXPOSURE:
None known to Tru-Test Manufacturing Company.

PRIMARY ROUTE (S) OF ENTRY:

☒ DERMAL ☒ INHALATION ☐ INGESTION

EMERGENCY AND FIRST AID PROCEDURES: EYES: Flush with large amounts of water. Seek medical attention.

SKIN: Wash with soap and water.

INHALATION: Remove to fresh air. Use artificial respiration if necessary. Get medical attention.

INGESTION: Do not induce vomiting, keep person warm and quiet. Get medical attention.

SECTION VI - REACTIVITY DATA

STABILITY:

☐ UNSTABLE ☒ STABLE

HAZARDOUS POLYMERIZATION

☐ MAY OCCUR ☒ WILL NOT OCCUR

HAZARDOUS DECOMPOSITION PRODUCTS: Carbon monoxide, Carbon dioxide.

CONDITIONS TO AVOID Isolate from heat and open flame.

INCOMPATIBILITY (MATERIALS TO AVOID) Avoid contact with strong oxidizing agents.

SECTION VII - SPILL OR LEAK PROCEDURES

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED

Eliminate all ignition sources. Contain spill, absorb liquid with clay, sand or floor absorbent. Prevent run-off to sewers, streams, and other bodies of water.

WASTE DISPOSAL METHOD

Contaminated absorbent may be deposited in a landfill in accordance with local, state and federal regulations.

SECTION VIII - SAFE HANDLING AND USE INFORMATION

RESPIRATORY PROTECTION - NIOSH/MSHA jointly approved air supplied respirator if TLV limits are exceeded. Approved mechanical filter to remove solid airborne particles of overspray during application.

VENTILATION - Provide sufficient mechanical (general and/or local exhaust) ventilation to maintain exposure below TLV.

PROTECTIVE GLOVES - Required to prevent prolonged or repeated contact.

EYE PROTECTION - Use of safety eyewear is recommended to prevent eye contact.

OTHER PROTECTIVE EQUIPMENT - Impervious clothing and boots are suggested to prevent prolonged or repeated skin contact.

HYGIENIC PRACTICES - Wash hands before eating, smoking or using the bathroom. Do not reuse contaminated clothing.

SECTION IX - SPECIAL PRECAUTIONS

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING: Keep away from heat, sparks and open flame. To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water filled, closed metal container.

OTHER PRECAUTIONS

Do not take internally. Avoid prolonged contact with skin. Containers should be grounded when pouring.

Avoid free fall of more than 2 - 3 inches when pouring.

The information contained in this MSDS is based on information and data provided by the supplier of the raw material used in the manufacture of this product. Although Tru-Test Manufacturing Company believes such information and data to be reliable, Tru-Test Mfg. Co. makes no warranty, expressed or implied, regarding the accuracy and completeness of such information and data.